

# Paint application chart Industry

Please observe the country-specific requirements of the paint manufacturer.



German Engineering



Please observe the country-specific requirements of the paint manufacturer.



SATAjet® 4000 B RP®  
(DIGITAL®)

SATAjet® 3000 K RP®

SATAjet® 1000 B RP®

Material

Nozzle size  
Atomisation pressure  
Material pressure

Nozzle size  
Atomisation pressure  
Material pressure

Nozzle size  
Atomisation pressure  
Material pressure

Material	Nozzle size Atomisation pressure Material pressure	Nozzle size Atomisation pressure Material pressure	Nozzle size Atomisation pressure Material pressure
High Build Epoxy Primer	---	2,0 1,8 - 2,5 bar (26,1 - 36,3 psi) 1,0 - 1,5 bar (14,5 - 21,8 psi)	2,0 - 2,5 1,8 - 2,0 bar (26,1 - 29,0 psi)
Awlgrip Topcoats G H line	1,0 - 1,3 1,8 - 2,0 bar (26,1 - 29,0 psi)	0,8 - 1,1 1,8 - 2,5 bar (26,1 - 36,3 psi) 0,5 - 1,0 bar (7,3 - 14,5 psi)	1,0 - 1,3 1,5 - 2,0 bar (21,8 - 29,0 psi)
Awlgrip HS N Line	1,0 - 1,3 1,8 - 2,0 bar (26,1 - 29,0 psi)	0,8 - 1,1 1,8 - 2,5 bar (26,1 - 36,3 psi) 0,5 - 1,0 bar (7,3 - 14,5 psi)	1,0 - 1,3 1,5 - 2,0 bar (21,8 - 29,0 psi)
Awlcraft SE E Line	1,0 - 1,3 1,8 - 2,0 bar (26,1 - 29,0 psi)	1,1 1,8 - 2,5 bar (26,1 - 36,3 psi) 0,5 - 1,0 bar (7,3 - 14,5 psi)	1,0 - 1,3 1,5 - 2,0 bar (21,8 - 29,0 psi)
545 Anti - Corrosive Epoxy Primer	---	1,3 - 1,6 1,8 - 2,0 bar (26,1 - 29,0 psi)	1,3 - 1,6 1,8 - 2,0 bar (26,1 - 29,0 psi)
Ultra Build Epoxy Primer	---	1,7 - 2,0 1,8 - 2,5 bar (26,1 - 36,3 psi) 0,8 - 1,0 bar (11,6 - 14,5 psi)	2,0 - 2,5 1,8 - 2,0 bar (26,1 - 29,0 psi)
Hullgard Extra Epoxy Primer	---	1,5 - 1,7 2,0 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,0 bar (11,6 - 14,5 psi)	1,8 - 2,5 1,5 - 2,0 bar (21,8 - 29,0 psi)
Hullgard Epoxy Primer	---	1,5 - 1,7 2,0 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,0 bar (11,6 - 14,5 psi)	1,8 - 2,5 1,5 - 2,0 bar (21,8 - 29,0 psi)
Epoxy Sprayable Fairing Compound	---	---	3,0 1,5 - 2,0 bar (21,8 - 29,0 psi)
Max Cor CF	0,8 - 1,0 1,8 - 2,0 bar (26,1 - 29,0 psi)	0,8 2,5 - 3,0 bar (36,3 - 43,5 psi) 0,5 - 1,0 bar (7,3 - 14,5 psi)	0,8 - 1,0 1,8 - 2,0 bar (26,1 - 29,0 psi)
Awlquik Epoxy Primer	---	1,1 1,8 - 2,5 bar (26,1 - 36,3 psi) 0,5 - 1,0 bar (7,3 - 14,5 psi)	1,3 1,8 - 2,0 bar (26,1 - 29,0 psi)
Quik Grip Fast Dry White Urethane	---	---	1,3 1,8 - 2,0 bar (26,1 - 29,0 psi)
Wash Primer CF	---	---	1,0 - 1,3 1,8 - 2,0 bar (26,1 - 29,0 psi)