

Paint application chart Industry

Please observe the country-specific requirements of the paint manufacturer.



German Engineering



Please observe the country-specific requirements of the paint manufacturer.



Material

SATAjet® 4000 B RP®
(DIGITAL®)

SATAjet® 3000 K RP®

SATAjet® 1000 B RP®

Nozzle size
Atomisation pressure
Material pressure

Nozzle size
Atomisation pressure
Material pressure

Nozzle size
Atomisation pressure
Material pressure

Material	SATAjet® 4000 B RP® (DIGITAL®) Nozzle size Atomisation pressure Material pressure	SATAjet® 3000 K RP® Nozzle size Atomisation pressure Material pressure	SATAjet® 1000 B RP® Nozzle size Atomisation pressure Material pressure
595TPC-EPX 2 K	---	2,0 3 - 4 bar (43,5 - 58,0 psi) 0,8 - 1 bar (11,6 - 14,5 psi)	---
648TPC-PUR 2 K	2,0 / 2,5 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 3 - 4 bar (43,5 - 58,0 psi) 0,8 - 1 bar (11,6 - 14,5 psi)	1,6 / 1,8 / 2,0 1,5 - 2 bar (21,8 - 29,0 psi)
821TPC-ACR	2,0 / 2,5 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 3 - 4 bar (43,5 - 58,0 psi) 0,8 - 1 bar (11,6 - 14,5 psi)	2,0 / 2,5 1,5 - 2 bar (21,8 - 29,0 psi)
699ACR- 2 K HS	2,0 / 2,5 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 3 - 4 bar (43,5 - 58,0 psi) 0,8 - 1 bar (11,6 - 14,5 psi)	2,0 / 2,5 1,5 - 2 bar (21,8 - 29,0 psi)