


DE BEER REFINISH	SATAjet® 5000 B HVLP	SATAjet® 5000 B RP®	SATAjet® 4000 B HVLP	SATAjet® 4000 B RP®	SATAjet® 3000 B HVLP	SATAjet® 3000 B RP®
1-15 Washprimer CF	1.3 / 1.4 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar
1-7510 Epoxyprimer white w/w	1.4 / 1.5 / 1.7 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 / 1.7 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 / 1.7 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar
8-145 HS Surfacer w/w	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar
8-746 High Productivity Primer w/w	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar
8-149 HS Tinting Surfacer w/w	1.3 2.0 bar	1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.3 1.8 - 2.0 bar
WaterBase Serie 900 or 900+	WSB / 1.3 2.0 bar	- -	WSB / 1.3 2.0 bar	- -	WSB / 1.3 2.0 bar	- -
BeroBase Serie 500	WSB / 1.3 2.0 bar	1.3 1.8 - 2.0 bar	WSB / 1.3 2.0 bar	1.3 1.8 - 2.0 bar	WSB / 1.3 2.0 bar	1.3 1.8 - 2.0 bar
8-104 HS Clear Coat	1.3 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar
8-414 HS420 Clear Coat	- -	1.2 / 1.3 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar
8-514 Speed Clear Coat / 8-614 Air Dry Clear Coat / 8-714 Supreme Clear Coat	- -	1.2 / 1.3 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.3 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.3 / 1.4 1.8 - 2.0 bar
Beromix 2000	1.3 / 1.4 2.0 bar	1.3 / 1.4 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.3 / 1.4 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.3 / 1.4 1.8 - 2.0 bar
BeroThane 3000 (HS420)	- -	1.2 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.4 1.8 - 2.0 bar

*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.



DE BEER REFINISH	SATA® minijet 4400® B HVLP	SATA® minijet 4400® B RP®	SATAminijet® 3000 B HVLP	SATAjet® 100 B F® RP®	SATAjet® 100 B F® HVLP	SATAjet® 100 B P®
1-15 Washprimer CF	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
1-7510 Epoxyprimer white	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
8-145 HS Surfacer	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
8-746 High Productivity Primer	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
8-149 HS Tinting Surfacer	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
WaterBase Serie 900 or 900+	0.8 SR / 1.0 SR 1.5 - 2.0 bar	- -	0.8 SR / 1.0 SR 1.5 - 2.0 bar	- -	- -	- -
BeroBase Serie 500	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.3 1.8 - 2.0 bar	-	- -
8-104 HS Clear Coat	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -
8-414 HS420 Clear Coat	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -
8-514 Speed Clear Coat / 8-614 Air Dry Clear Coat / 8-714 Supreme Clear Coat	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -
Beromix 2000 and 3000 Berothane (HS)	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -

*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.