

Paint application chart Wall painter

Please observe the country-specific requirements of the paint manufacturer.



German Engineering



Please observe the country-specific requirements of the paint manufacturer.



Material	SATAJet® 4000 B HVLP (DIGITAL)	SATAJet® 4000 B RP® (DIGITAL®)	SATAJet® 3000 K RP®
	Nozzle size Atomisation pressure Material pressure	Nozzle size Atomisation pressure Material pressure	Nozzle size Atomisation pressure Material pressure
SIGMASTAR gloss/satin	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMA ZINCOLOR	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMA Master-Vorlack	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMA ALLGRUND	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMATORNO primer 10 % verdünnt H2O	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMATORNO semigloss 10 - 15 % verdünnt H2O	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMA CONTOUR Aqua-PU gloss/satin/matt 10 % verdünnt H2O	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMULTO metallic 10 % verdünnt H2O	1,9 3 bar (43,5 psi)	2,0 1,8 - 2 bar (26,1 - 29,0 psi)	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMA CONTOUR Aqua-PU Spray satin	---	---	1,3 / 1,5 2 - 2,5 bar (29,0 - 36,3 psi) 0,8 - 1,5 bar (11,6 - 21,8 psi)
SIGMULTO Aquasphere	---	---	3,0SK79 0,3 bar (4,4 psi) 0,8 bar (11,6 psi)